



FLUOROWRAP®

mA Medium Contrast Laser Mark-able

Engineered for High Performance Insulation

Extruded PTFE Film

FLUOROWRAP® mA Medium Contrast Laser Mark-able Film is engineered to meet the most demanding requirements of the aerospace industry. Saint-Gobain mA film meets the OEM industry requirements for contrast levels before and after heat aging. Saint-Gobain's extrusion process provides the longest splice free/joint free lengths available for improved insulation integrity and higher physical properties that support faster tape wrapping speeds. FLUOROWRAP® mA films are manufactured with ASTM D4895 compliant resins.

Features/Benefits

- Contrast Ratio: 60% before heat aging, 40% after heat aging
- Long length splice free/joint free films
- Tight thickness tolerance
- High tensile strength
- White color
- RoHS and REACH compliant


Availability

FLUOROWRAP® mA films are available on industry standard 3" (76 mm) ID cores in flat-pad, traverse wound and StableEdge™ packages.

Slit widths are available from 0.10" (2.5 mm) and wider. Customized solutions available.

Applications

Laser marked aerospace wire and cable construction for on-board flight control, power, communication and entertainment systems



SAINT-GOBAIN

FLUOROWRAP® mA Properties

Performance tests are run using standard test procedures.
The values presented are typical values and should not be used for specification purposes.

Property	English Units	Metric Units
Thickness	2.5 mil	0.064 mm
Tolerance	+/- 5 %	+/- 5%
Density	1.60 g/cm ³	
Tolerance	+/- 0.5 g/cm ³	
Tensile Strength MD (minimum)	2,900 psi	20 MPa
Tensile Strength TD (minimum)	247 psi	1.7 MPa
Elongation MD (minimum)	60 %	
Elongation TD (minimum)	800 %	
Contrast (Initial)	60 %	
Contrast (after heat age)	40 %	
Splice Free Roll Lengths	1,199 LY	1,096 M

FLUOROWRAP and StablEdge™ are registered trademarks.



Saint-Gobain

AMERICAS
Tel: (800) 962-2666
(518) 686-7301

EUROPE
Tel: +44 (0) 1706-746900

ASIA
Tel: (886) 2-2503-4201

www.films.saint-gobain.com

AMERICAS: 14 McCaffrey Street, Hoosick Falls, NY 12090, USA

EUROPE: Bay 3 Transpennine Industrial Estate, Gorrels Way, Rochdale, OL11 2PX, UK

ASIA: Room 302,3F-1, 147 Jianguo North Road, Section 2, Taipei, Taiwan, 104

The data and details in this document were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to obtain the latest version of the product data sheet. This data sheet is not a specification and does not assure specific product characteristics or make reference to the suitability of the product for a specific application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, use and conversion of this product are the user's responsibility.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse or inability to use this product(s).

SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform their own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.